

Planeo 4065



23 1/2 in x 4 in or 600 mm x 100 mm

Technical datasheet



Planeo 4065

WHS: Wood hybrid system

Geolam®

Architectural Eco-Technology



Section tolerances in mm: +/- 2.0 mm or +/- 3/32 in

The outer wpc layer is sanded. The provided dimensions are average thickness (as well for all drawing in that document)

Fire rating:

On request:

ASTM E-84 class A

Euroclass NF EN 135011 : B, s3-d0

Euroclass NF EN 135011 : A2, s3-d0

NFP 92 -507 : M2 or M1

Surfaces finish: Sanded

Other surface textures available on request. Sanding finish and/or shading may vary between runs. WPC thickness may vary in compliance with flame test requirements.

Profiles fastening and installation: Planeo boards cannot be cut within the bolts at either board end. Refer to our website www.geolam.com

Technical information may change without warning.

Standard length: 9 ft 10 in | 3.0 m

On order any length from: 7 ft to 27 ft | 2.15 m to 8.25 m

Weight: 10.48 lb/ft | 15.60 kg/m

Secondary moment Ix (cm⁴): 757.72

Secondary moment Iy (cm⁴): 14361.87

Section modulus Z+x (cm³): 156.23

Section modulus Z-x (cm³): 156.23

Section modulus Z+y (cm³): 481.13

Section modulus Z-y (cm³): 481.13

Core in anodized aluminum alloy: A6063S-T5 Serie 6000

Coefficient of Thermal Expansion (20-100°C):

23.4 μm/m/°C

Modulus of Elasticity: 68.9 GPa

Max Tensile Strength: 186 Mpa

Carbon Footprint:

WPC : 1.54 kg CO₂ /Kg WPC

Alu : 0.87 kg CO₂ /Kg Alu



Teak



Limba



Rosewood



Wenge



Bilinga




Carbon



Ivory



Any color on request



Technical specifications, dimensions in mm

Weight (lb/ft)	10.48	Cross section coefficient Z+x (cm ³)	156.23	Wood hybrid system WHS	Type 1.0
Cross section, secondary moment Ix (cm ⁴)	757.72	Cross section coefficient Z-x (cm ³)	156.23	Planeo 4065	
Cross section, secondary moment Iy (cm ⁴)	14361.87	Cross section coefficient Z+y (cm ³)	481.13		
		Cross section coefficient Z-y (cm ³)	481.23		