











Section tolerances in mm: +/- 2.0 mm or +/- 3/32 in

The outer wpc layer is sanded. The provided dimensions are average thickness (as well for all drawing in that document)

Fire rating: <u>On request:</u> ASTM E-84 class A Euroclass NF EN 135011 : B, s3-d0 Euroclass NF EN 135011 : A2, s3-d0 NFP 92 -507 : M2 or M1		
Surfaces finish: Sanded Other surface textures available on request. Sanding finish and/or shading may vary between runs. WPC thickness may vary in compliance with flame test requirements.	Teak	Limba
Profiles fastening and installation: Planeo boards cannot be cut within the bolts at either board end. Refer to our website www.geolam.com Technical information may change without warning.	Rosewood	Wenge
Standard length: 9 ft 10 in 3.0 m On order any length from: 7 ft to 27 ft 2.15 m to 8.25 m		
Neight: 3.77 lb/ft 5.61 kg/m		
econdary moment lx (cm ⁴): 19.85		
econdary moment ly (cm ⁴): 2327.63		
ection modulus Z+x (cm³): 15.37	Bilinga	Carbon
ection modulus Z-x (cm³): 14.1		
Section modulus Z+y (cm³): 107.76		
Core in anodized aluminum alloy: A6063S-T5 Serie 6000		
Coefficient of Thermal Expansion (20-100°C): 3.4 μm/m/°C		
Modulus of Elasticity: 68.9 GPa	lvory	Any color on request
Max Tensile Strength: 186 Mpa		

Carbon Footprint:

 $\label{eq:WPC:1.54 kg CO_2/Kg WPC} \textbf{WPC:} 1.54 kg \ \textbf{CO}_2/\textbf{Kg WPC} \textbf{Alu:} 0.87 kg \ \textbf{CO}_2/\textbf{Kg Alu}$